

COATING UV6100 Flexo FB Gloss

Galaxy Coating UV6100 is a radical curing UV varnish with a high reactivity. The foil stampable coating can be used in inline applications over UV inks. The coating can be used in off-line applications. In the fully cured print the coating shows low odour.

Application: Recommended coating weight 2 – 4 grms/m² (wet)
 Suitable for paper (coated), board, certain treated foils
 Not recommended for hi absorbent substrates and plastics
 Suitable for conventional anilox and roller coater

Use: Use solvent and alkali resistant inks
 Press ready
 Optimal properties obtained 24hrs after printing
 Not suitable for food- and other sensitive packaging. Suitable for secondary packaging only if a functional barrier avoid migration (global and specific) of substances to the content. Before bringing into circulation corresponding migration tests shall be conducted.

Performance key:	Gloss	10	1 matt – 10 highest gloss
	Cure speed	4	
	Slip	3	
	Rub resistance	4	
	Block resistance	5	
	Glueability	5	Specific films to be tested
	Solvent resistance	4	Specific conditions to be tested

** 1 (Slow / Low) – 5 (Fast / High) **

Typical constants:	Viscosity	1.8 – 2.2 P @ 25°C	
	Specific gravity	1.10 g/cm ³	± 0.05
	Apearance	Brownish, hazy liquid	

Storage conditions: Store away from excessive heat, out of direct sunlight and in closed packaging. Prefered conditions between 15 - 20°C

Cleaning: Use a proper UV-wash, UV-Wash UV4000-IQ-S

Shelf life: In unopened, original packaging, 8 months from manufacturing date

Version: 01-2012

The information provided in this technical data sheet is to inform our customers. A successful application depends on a variety of different factors. Therefore the advice given in this technical data sheet cannot be used as basis for claims. Our recommendation is where possible to perform tests before entering production runs.