

# PrintCare

## RUBBERBLANKETS

ISO 9001:2008

### StripperOne

For waterbased coating applications


Converted by AtéCé Graphic Products

**AtéCé**  
GRAPHIC PRODUCTS

[www.atece.com](http://www.atece.com)

AtéCé Graphic Products  
Molenwerf 14 - 1911 DB Uitgeest  
P.O. Box 49 - 1910 AA Uitgeest  
The Netherlands

T +31 (0) 251 - 319109  
F +31 (0) 251 - 315850  
E [info@atece.com](mailto:info@atece.com)



# PrintCare Rubber Blankets

## StripperOne

PrintCare StripperOne is characterized by easy to cut & peel and is suitable for waterbased coating. Due to its new developed fabrics you have sharp edges and trouble free stencil preparations. The PrintCare StripperOne can be cut manually or by CAD like our PrintCare Plotter

<b>INNOVATION</b>	AtéCé a major global <b>blanket converter</b> leads the industry with innovative blanket development. Our commitment is to continue developing and delivering innovative products that improve print results.
<b>TECHNOLOGY</b>	PrintCare compressible layer is the most advanced production technique available and is the next generation in blanket manufacturing.
<b>RELIABILITY</b>	The consistency and quality of our new PrintCare compressible layer technology and improved gauge control from our advanced buffing techniques gives a superior result, faster recovery on press, improved smash resistance and reduces gauge loss.
<b>VALUE</b>	Improvements provided by PrintCare compressible layer means exceptional long life from the blanket, improving production time and reducing down-times on press.
<b>ECOLOGY</b>	PrintCare compressible layer production is solvent free, another first in innovation from AtéCé.

## surface

Rubber compound	For sheetfed application
Surface finish	Micro-ground and polished
Roughness (Ra)	0,9 µm
Colour	Blue

## construction

Compressible layer design	Microsphere PrintCare
Nominal thickness	1.96 mm
Fabric plies	3 plies

## physical property

Thickness range	1.96 ± 0.02 mm
Overall hardness (Shore A)	75 °
Compressibility @ 180N	200 µm
Tensile strength at break	> 40 N/mm
Elongation at 10 N/mm	< 0,70%
Stencil depth	0.80 mm

